


AMENDMENT(S) TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in this application:

Listing of Claims:

1. (Previously presented) A composition comprising a mixture of racemic and meso isomers of metallocene compounds having the formula:








where L^1 and L^2 are identical or different ligands and are each a substituted mononuclear or polynuclear hydrocarbon radical selected from the group consisting of substituted cyclopentadienyl, indenyl, tetrahydroindenyl, azurenyl, fluorenyl, azapentalenyl, thiapentalenyl or oxapentalenyl, which form a sandwich structure with atom M^1 therebetween,

R^1 and R^2 are identical or different and are each a hydrogen atom, an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an aryloxy group of from about 6 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an OH group, a halogen atom, or a NR_2^{32} group, where R^{32} is an alkyl group of from 1 to about 10 carbon atoms or an aryl group of from 6 to about 14 carbon atoms, or R^1 and R^2 form one or more ring system(s),

M^1 is a metal of group IVb of the Periodic Table of the Elements,

R^9 is a bridge between the ligands L^1 and L^2 having one of the structures:





where R^{40} and R^{41} , are identical or different, with or without heteroatoms, when R^{40} and R^{41} are identical they are selected from the group consisting of a cyclic or non-cyclic alkyl group having from 2 to about 30 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from about 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, when R^{40} and R^{41} are different one of either R^{40} and R^{41} is selected from the group consisting of a cyclic or non-cyclic alkyl group having from 4 to about 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, and the other of R^{40} and R^{41} is selected from the group consisting of a cyclic or non-cyclic alkyl group having from 1 to 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms,

M^{12} is silicon, germanium or tin, and

wherein the mixture of racemic and meso isomers as synthesized has a weight ratio of racemic to meso isomers of greater than 5:1.

2. (Original) The composition of Claim 1 wherein L^1 is a substituted cyclopentadienyl, indenyl, tetrahydroindenyl, azurenyl, fluorenyl, azapentalenyl, thiapentalenyl or oxapentalenyl,

L^2 is a substituted indenyl, tetrahydroindenyl, azurenyl, fluorenyl, azapentalenyl, thiapentalenyl or oxapentalenyl, and

the bridging unit R^9 is $R^{40}R^{41}Si=$, $R^{40}R^{41}Ge=$, $R^{40}R^{41}C=$ or $-(R^{40}R^{41}C-CR^{40}R^{41})-$, where R^{40} and R^{41} are identical or different and are each an alkyl group of from 2 to about 30 carbon atoms, an arylalkyl group of from 7 to about 14 carbon atoms or an alkylaryl group of from 7 to about 14 carbon atoms.

3. (Currently amended) The composition of Claim 1 wherein R^{40} and R^{41} are different, R^{40} is a C_4 - C_{30} ~~hydrocarbon~~ cyclic or non-cyclic alkyl group and R^{41} is a C_1 - C_{30} ~~hydrocarbon~~ cyclic or non-cyclic alkyl group.

4. (Currently amended) The composition of Claim 1 wherein L^1 and L^2 are identical or different and are each a substituted indenyl, azurenyl, fluorenyl, azapentalenyl, thiapentalenyl or oxapentalenyl, and

the bridging unit R^9 is $R^{40}R^{41}Si=$ or $R^{40}R^{41}Ge=$, where R^{40} and R^{41} are identical or different and are propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, ~~cyclopentyl~~ cyclopentyl, or cyclohexyl.


5. (Currently amended) The composition of Claim 4 wherein R^{40} and R^{41} are different, R^{40} is butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~cyclopentadienyl~~, or cyclohexyl, and R^{41} is methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, or cyclohexyl.

6. (Original) The composition of Claim 1 wherein the weight ratio of racemic to meso isomers is greater than 10:1.

7. (Original) The composition of Claim 1 wherein the weight ratio of racemic to meso isomer is greater than 15:1.

8. (Original) The composition of Claim 1 wherein the weight ratio of racemic to meso isomers is greater than 20:1.

9. (Currently amended) The composition of Claim 1 wherein the compound has the formula:



(formula 1b)

where R^3 , R^4 , R^5 , R^6 , R^7 , R^8 and also $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched group, with or without heteroatoms, selected from an alkyl group of from 1 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or an arylalkenyl group of from 8 to about 40 carbon atoms, or a substituted or unsubstituted alkylsilyl or arylsilyl group, with the proviso that R^3 and $R^{3'}$ are not hydrogen, and wherein two adjacent

radicals R^5 , R^6 or $R^{5'}$, $R^{6'}$, or R^6 , R^7 or $R^{6'}$, $R^{7'}$, or R^7 , R^8 or $R^{7'}$, $R^{8'}$ can form a hydrocarbon ring system.

10. (Original) The composition of Claim 9 wherein at least one of R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ includes a heteroatom selected from the group consisting of Si, B, Al, O, S, N, P, F, Cl and Br.

11. (Original) The composition of Claim 9 where

M^1 is zirconium or hafnium,

R^1 and R^2 are identical or different and are an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, or a halogen atom, or R^1 and R^2 together form one or more ring system(s),

R^3 and $R^{3'}$, are identical or different and are each a linear, cyclic or branched group, with or without a halogen, selected from the group consisting of an alkyl group of from 1 to about 10 carbon atoms and an alkenyl group of from 2 to about 10 carbon atoms,

R^4 , R^5 , R^6 , R^7 , R^8 and also $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom, or a substituted or unsubstituted alkylsilyl or arylsilyl group, or a linear, cyclic or branched group, with or without heteroatoms, or an alkyl group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 10 carbon atoms, or the two adjacent radicals R^5 , R^6 and $R^{5'}$, $R^{6'}$ may form a hydrocarbon ring system,


R^9 is $R^{40}R^{41}Si=$, $R^{40}R^{41}Ge=$, $R^{40}R^{41}C=$ or $-(R^{40}R^{41}C-CR^{40}R^{41})-$, where R^{40} and R^{41} are identical or different and are each an alkyl group of from 2 to about 30 carbon atoms, an arylalkyl group of from 7 to about 14 carbon atoms or an alkylaryl group of from 7 to about 14 carbon atoms.

12. (Currently amended) The composition of Claim 9 wherein R^{40} and R^{41} are different, R^{40} is ~~a hydrocarbon~~ an alkyl group of from 4 to about 30 carbon atoms, and R^{41} is a ~~hydrocarbon~~ an alkyl group of from 1 to about 30 carbon atoms.

13. (Currently amended) The composition of Claim 9 wherein
 M^1 is zirconium,
 R^1 and R^2 are identical or different and are methyl, chlorine or phenolate,
 R^3 and $R^{3'}$, are identical or different and are each a linear, cyclic or branched group, with or without a halogen, ~~which is~~ and are selected from the group consisting of an alkyl group of from 1 to about 10 carbon atoms and an alkenyl group of from 2 to about 10 carbon atoms,
 R^4 and ~~also~~ $R^{4'}$ are hydrogen,
 R^5 , R^6 , R^7 , R^8 and ~~also~~ $R^{5'}$, $R^{6'}$, $R^{7'}$, $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched alkyl group of from 1 to about 10 carbon atoms, or an aryl group of from 6 to about 10 carbon atoms, or the two adjacent radicals R^5 , R^6 and $R^{5'}$, $R^{6'}$ form a hydrocarbon ring system, and
 R^9 is $R^{40}R^{41}Si=$ or $R^{40}R^{41}Ge=$, where R^{40} and R^{41} are identical or different and are propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~eyelopentadienyl~~ or cyclohexyl.

14. (Currently amended) The composition of Claim 13 wherein R^{40} and R^{41} are different and R^{40} is butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~eyelopentadienyl~~ or cyclohexyl and R^{41} is methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~eyelopentadienyl~~ or cyclohexyl.

15. (Currently amended) The composition of Claim 1 wherein the compound has the formula:



(formula 1c)

where R^3 , R^4 , R^5 , R^6 , R^7 , R^8 and also $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom, or a linear, cyclic or branched hydrocarbon group with or without heteroatoms and selected from an alkyl group of from 1 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or an arylalkenyl group of from 8 to about 40 carbon atoms, or a substituted or unsubstituted alkylsilyl or arylsilyl group, with the proviso that R^3 and $R^{3'}$ are not hydrogen and that R^5 and $R^{5'}$ are identical or different and are each a substituted or unsubstituted aryl group of from 6 to ~~about 40~~ 20 carbon atoms.

16. (Original) The composition of Claim 15 wherein at least one of R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ includes a heteroatom selected from the group consisting of Si, B, Al, O, S, N, P, F, Cl and Br.

17. (Currently amended) The composition of Claim 15 wherein M^1 is zirconium or hafnium,

R^1 and R^2 are identical or different and are an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms or a halogen atom, or R^1 and R^2 together form one or more ring system(s), and

R^3 and $R^{3'}$, are identical or different and are each a linear, cyclic or branched group, with or without a halogen, and selected from the group consisting of an alkyl group of from 1 to about 10 carbon atoms and an alkenyl group of from 2 to about 10 carbon atoms, and

R^4 , R^6 , R^7 , R^8 and also $R^{4'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched alkyl group of from 1 to about 10 carbon atoms, with or without a heteroatom,

R^5 and $R^{5'}$ are identical or different and are each a substituted aryl group of from 6 to about 40 20 carbon atoms,

R^9 is $R^{40}R^{41}Si=$, $R^{40}R^{41}Ge=$, $R^{40}R^{41}C=$ or $-(R^{40}R^{41}C-CR^{40}R^{41})-$, where R^{40} and R^{41} are identical or different and are each an alkyl group of from 2 to about 30 carbon atoms, an arylalkyl group of from 7 to about 14 carbon atoms or an alkylaryl group of from 7 to about 14 carbon atoms.

18. (Currently amended) The composition of Claim 15 wherein R^{40} and R^{41} are different, R^{40} is ~~a hydrocarbon~~ a cyclic or non-cyclic alkyl group of from 4 to about 30 carbon atoms and R^{41} is ~~a hydrocarbon~~ a cyclic or non-cyclic alkyl group of from 1 to about 30 carbon atoms.

19. (Currently amended) The composition of Claim 15 wherein M^1 is zirconium,
 R^1 and R^2 are identical or different and are an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms or a halogen atom, or R^1 and R^2 together form one or more ring system(s),
 R^3 and $R^{3'}$ are identical or different and are each a linear, cyclic or branched methyl, ethyl, propyl, butyl, pentyl or hexyl,
 R^4 and $R^{4'}$ are both hydrogen,

R^6 , R^7 , R^8 and also $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched alkyl group of from 1 to about 10 carbon atoms, with or without a heteroatom,


R^5 and $R^{5'}$ are identical or different and are naphthyl, para-(C_1 - C_{10} -alkyl)phenyl, para-(C_1 - C_{10} -fluoroalkyl)phenyl, meta-(C_1 - C_{10} -alkyl)phenyl, meta-(C_1 - C_{10} -alkyl)phenyl, meta, meta'-(C_1 - C_{10} -alkyl)₂phenyl or meta, meta'-(C_1 - C_{10} -fluoroalkyl)₂phenyl, and

R^9 is $R^{40}R^{41}Si=$ or $R^{40}R^{41}Ge=$, where R^{40} and R^{41} are identical or different and are ~~propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, or cyclohexyl~~.

20. (Original) The composition of Claim 19 wherein R^1 and R^2 are identical and are methyl, chlorine, or phenolate.

21. (Currently amended) The composition of Claim 19 wherein R^{40} and R^{41} are different and R^{40} is butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~cyclopentadienyl~~ or cyclohexyl, and R^{41} is methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, or cyclohexyl.

22. (Original) The composition of Claim 1 wherein the compound has the formula:



(formula 1d)

where R^4 , R^5 , R^6 , R^7 , R^8 and also $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom, a linear, cyclic or branched hydrocarbon group, with or without heteroatoms, and selected from the group consisting of an alkyl group of from 1 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or an arylalkenyl group of from 8 to about 40 carbon atoms, or a substituted or unsubstituted alkylsilyl or arylsilyl group, with the proviso that R^5 and $R^{5'}$ are identical or different and are each a substituted aryl group of from 6 to about 40 carbon atoms,

R^3 is a linear hydrocarbon group, with or without a heteroatom, and selected from the group consisting of an alkyl group of from 1 to about 20 carbon atoms, an aryl substituted alkyl group of from 7 to about 40 carbon atoms and an aryl substituted alkenyl group of from 8 to about 40 carbon atoms,

$R^{3'}$ is a hydrocarbon group, cyclic or branched in the α position, with or without a heteroatom, and selected from the group consisting of an alkyl group of from 3 to about 20 carbon atoms, an alkenyl group of from 3 to about 20 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl

group of from 7 to about 40 carbon atoms and an arylalkenyl group of from 8 to about 40 carbon atoms.

23. (Currently amended) The composition of Claim 22 wherein M^1 is zirconium or hafnium,

R^1 and R^2 are identical or different and are an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms or a halogen atom, or R^1 and R^2 together form one or more ring system(s),

R^3 is a linear alkyl group of from 1 to about 10 carbon atoms or an alkenyl group of from 2 to about 10 carbon atoms, with or without a halogen,

$R^{3'}$ is a hydrocarbon group, cyclic or branched in the α position and selected from the group consisting of an alkyl group of from 3 to about 20 carbon atoms and cyclic or branched in the α position, an alkenyl group of from 3 to about 20 carbon atoms, or an alkylaryl group of from 7 to about 20 carbon atoms,

R^4 , R^6 , R^7 , R^8 and also $R^{4'}$, $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched alkyl group of from 1 to about ~~20~~ 10 carbon atoms, with or without a halogen,

R^5 and $R^{5'}$ are identical or different and are each a substituted aryl group of from 6 to about 40 carbon atoms, selected from para-(C_1 - C_{10} -alkyl)phenyl, meta-(C_1 - C_{10} -alkyl)phenyl, meta, meta'-(C_1 - C_{10} -alkyl)₂phenyl, and

R^9 is $R^{40}R^{41}Si=$, $R^{40}R^{41}Ge=$, $R^{40}R^{41}C=$ or $-(R^{40}R^{41}C-CR^{40}R^{41})-$, where R^{40} and R^{41} are identical or different and are each an alkyl group of from 2 to about 30 carbon atoms, an arylalkyl group of from 7 to about 14 carbon atoms or an alkylaryl group of from 7 to about 14 carbon atoms.

24. (Currently amended) The composition of Claim 22 wherein R^{40} and R^{41} are different, R^{40} is ~~a hydrocarbon~~ a cyclic or non-cyclic alkyl group of from 4 to about 30 carbon atoms and R^{41} is ~~a hydrocarbon~~ a cyclic or non-cyclic alkyl group of from 1 to about 30 carbon

atoms.

25. (Currently amended) The composition of Claim 22 where M^1 is zirconium, R^1 and R^2 are identical and are methyl, chlorine, or phenolate, R^3 is methyl, ethyl, n-propyl, n-butyl, n-pentyl or n-hexyl, $R^{3'}$ is iso-propyl, ~~iso-butyl~~, sec-butyl, cyclobutyl, 1-methyl-butyl, 1-ethyl-butyl, 1-methyl-pentyl, cyclopentyl, cyclohexyl, cyclopent-2-enyl, cyclopent-3-enyl, cyclohex-2-enyl, cyclohex-3-enyl or para-methyl-cyclohexyl,

R^4 and also $R^{4'}$ are hydrogen, and

R^6 , R^7 , R^8 and also $R^{6'}$, $R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom or a linear, cyclic or branched alkyl group of from 1 to about 10 carbon atoms, with or without a heteroatom, and,

R^5 and $R^{5'}$ are identical or different and are p-isopropyl-phenyl, p-tert[[.]]-butyl-phenyl, p-s-butyl-phenyl, p-cyclohexyl-phenyl, p-trimethylsilyl-phenyl, p-adamantyl-phenyl, ~~p-(trifluor)trimethyl-phenyl~~ ~~p-(trifluoro)trimethyl-phenyl~~, m,m'-dimethyl-phenyl, and

R^9 is $R^{40}R^{41}Si=$ or $R^{40}R^{41}Ge=$, ~~where R^{40} and R^{41} are identical or different and are propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, or cyclohexyl.~~

26. (Currently amended) The composition of Claim 25 wherein R^{40} and R^{41} are different and R^{40} is butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, ~~cyclopentadienyl~~ or cyclohexyl, and R^{41} is methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, cyclopentyl, or cyclohexyl.

27. (Currently amended) The composition of Claim 1 wherein the synthesized compound is selected from the group consisting of:

A-(2-isopropyl-4-(p-isopropyl-phenyl)indenyl)(2-methyl-4-(p-isopropyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2-methyl-4-(p-tert-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2-methyl-4-(p-tert-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,7-dimethyl-4-(p-tert-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,7-dimethyl-4-(p-tert-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,5,6,7-tetramethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,5,6,7-tetramethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-6-methyl-4-(p-tert-butyl-phenyl)indenyl)(2,6-dimethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-6-methyl-4-(p-tert-butyl-phenyl)indenyl)(2,6-dimethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-sec-butyl-phenyl)indenyl)(2-methyl-4-(p-sec-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-sec-butyl-phenyl)indenyl)(2-methyl-4-(p-sec-butyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-cyclohexyl-phenyl)indenyl)(2-methyl-4-(p-cyclohexyl-phenyl) indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-trimethylsilyl-phenyl)indenyl)(2-methyl-4-(p-trimethylsilyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-adamantyl-phenyl)indenyl)(2-methyl-4-(p-adamantyl-phenyl)indenyl)-zirconiumdichloride,

A-(2-isopropyl-4-(p-tris(trifluoromethyl)methyl-phenyl)indenyl)(2-methyl-4-(p-tris(trifluoromethyl)methyl-phenyl)indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-phenyl-indenyl)(2-methyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-phenyl-indenyl)(2-methyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride;

~~A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2-methyl-4-phenyl-indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2-methyl-4-phenyl-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,7-dimethyl-4-phenyl-indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,7-dimethyl-4-phenyl-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,5,6,7-tetramethyl-4-phenyl-indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-(p-tert-butyl-phenyl)indenyl)(2,5,6,7-tetramethyl-4-phenyl-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-6-methyl-4-(p-tert-butyl-phenyl)indenyl)(2,6-dimethyl-4-phenyl-indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-6-methyl-4-(p-tert-butyl-phenyl)indenyl)(2,6-dimethyl-4-phenyl-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-phenyl-indenyl)(2,7-dimethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-phenyl-indenyl)(2,7-dimethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-phenyl-indenyl)(2,5,6,7-tetramethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride;~~

A-(2-isopropyl-4-phenyl-indenyl)(2,5,6,7-tetramethyl-4-(p-tert-butyl-phenyl)indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-6-methyl-4-phenyl-indenyl)(2,6-dimethyl-4-(p-tert-butyl-phenyl)-indenyl)-zirconiumdichloride,~~

A-(2-isopropyl-6-methyl-4-phenyl-indenyl)(2,6-dimethyl-4-(p-tert-butyl-phenyl)-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-(p-tert-butyl-phenyl)-indenyl)(2-methyl-4-(4-naphthyl)-indenyl)-indenyl)-zirconiumdichloride,~~

A-(2-isopropyl-4-(p-tert-butyl-phenyl)-indenyl)(2-methyl-4-(4-naphthyl)-indenyl)-indenyl)-zirconiumdichloride,

~~A-(2-isopropyl-4-(4-naphthyl)-indenyl)-indenyl)(2-methyl-4-(p-tert-butyl-phenyl)-indenyl)-zirconiumdichloride,~~

A-(2-isopropyl-4-(4-naphthyl)-indenyl)-indenyl)(2-methyl-4-(p-tert-butyl-phenyl)-indenyl)-zirconiumdichloride,

A-bis(4-naphthyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-benzo-indenyl)zirconiumdichloride

A-bis(2-methyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-(1-naphthyl)-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-(2-naphthyl)-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-phenyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-t-butyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-isopropyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-ethyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4-acenaphth-indenyl)zirconiumdichloride,

A-bis(2,4-dimethyl-indenyl)zirconiumdichloride,

A-bis(2-ethyl-indenyl)zirconiumdichloride,

A-bis(2-ethyl-4-ethyl-indenyl)zirconiumdichloride,

A-bis(2-ethyl-4-phenyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4,6-diisopropyl-indenyl)zirconiumdichloride,

A-bis(2-methyl-4,5-diisopropyl-indenyl)zirconiumdichloride,

A-bis(2,4,6-trimethyl-indenyl)zirconiumdichloride,

A-bis(2,5,6-trimethyl-indenyl)zirconiumdichloride,
A-bis(2,4,7-trimethyl-indenyl)zirconiumdichloride,
A-bis(2-methyl-5-isobutyl-indenyl)zirconiumdichloride,
A-bis(2-methyl-5-*t*-butyl-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(*tert*-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4-trifluoromethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4-methoxy-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4-*tert*-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4-trifluoromethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4-methoxy-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4-*tert*-butyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-methyl-4-(4-methyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-methyl-4-(4-ethyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-methyl-4-(4-trifluoromethyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-methyl-4-(4-methoxy-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-ethyl-4-(4-*tert*-butyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-ethyl-4-(4-methyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-ethyl-4-(4-ethyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-ethyl-4-(4-trifluoromethyl-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-ethyl-4-(4-methoxy-phenyl)-indenyl)zirconiumdimethyl,
A-bis(2-isopropyl-4-(*tert*-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4-trifluoromethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4-methoxy-phenyl)-indenyl)zirconiumdichloride,

A-bis(2-isopropyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)hafniumdichloride,
A-bis(2-isopropyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)titaniumdichloride,
A-bis(2-isopropyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-pentyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-cyclohexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-isopropyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)hafniumdichloride,
A-bis(2-methyl-4-(4'-tert[.]-butyl-phenyl)-indenyl)titaniumdichloride,
A-bis(2-methyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-methyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-ethyl-phenyl)-indenyl)zirconiumdichloride,

A-bis(2-ethyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-pentyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-cyclohexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-ethyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-phenyl-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-iso-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-cyclohexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-propyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-phenyl-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-ethyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-iso-propyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-hexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-cyclohexyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-n-butyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-hexyl-4-phenyl-indenyl)zirconiumdichloride,
A-bis(2-hexyl-4-(4'-methyl-phenyl)-indenyl)zirconiumdichloride,
A-bis(2-hexyl-4-(4'-ethyl-phenyl)-indenyl)zirconiumdichloride,

A-bis(2-hexyl-4-(4'-n-propyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-iso-propyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-n-butyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-n-hexyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-cyclohexyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-sec-butyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-hexyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdichloride,
 A-bis(2-methyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumbis(dimethylamine),
 A-bis(2-ethyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdibenzyl,
 A-bis(2-methyl-4-(4'-tert[.])butyl-phenyl)-indenyl)zirconiumdimethyl,
 A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-methyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-5-azapentalene)(2-methyl-4-(4'-methyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-6-azapentalene)(2-methyl-4-(4'-methyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-ethyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-propyl-phenyl)-indenyl)-zirconiumdichloride,
 A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-isopropyl-phenyl)-indenyl)-zirconiumdichloride,
 A-(2-methyl-6-azapentalene)(2-methyl-4-(4'-isopropyl-phenyl)-indenyl)-zirconiumdichloride,
 A-(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-isopropyl-phenyl)-indenyl)-
 zirconiumdichloride,
 A-(2-methyl-6-oxapentalen)(2-methyl-4-(4'-isopropyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-butyl-phenyl)-indenyl)- zirconiumdichloride,
 A-(2-methyl-5-thiapentalene)(2-methyl-4-(4'-n-butyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-butyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-s-butyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-oxapentalene)(2-methyl-4-(4'-s-butyl-phenyl)-indenyl) zirconiumdichloride,
 A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-tert-butyl-phenyl)-indenyl)- zirconiumdichloride,
 A-(2-methyl-6-azapentalene)(2-methyl-4-(4'-tert-butyl-phenyl)-indenyl)- zirconiumdichloride,
 A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-pentyl-phenyl)-indenyl)- zirconiumdichloride,

A-(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-pentyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-pentyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-hexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-hexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-hexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-n-hexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-n-hexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-cyclohexyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-trimethylsilyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-trimethylsilyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-5-thiapentalene)(2-methyl-4-(4'-trimethylsilyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-6-thiapentalene)(2-methyl-4-(4'-trimethylsilyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-adamantyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-adamantyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-6-thiapentalene)(2-methyl-4-(4'-adamantyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-adamantyl-phenyl)-indenyl)-zirconiumdichloride,
A-(2-methyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methyl-phenyl)-indenyl)-zirconiumdichloride,

A-(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methyl-phenyl)-indenyl) zirconiumdichloride,

A-(2-methyl-4-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methyl-phenyl)-indenyl)zirconiumdichloride,

A-(2-methyl-6-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methyl-phenyl)-indenyl)zirconiumdichloride,

A-(2-methyl-4-azapentalene)(2-ethyl-4-(4'-tert-butyl-phenyl)-indenyl)- zirconiumdichloride,

A-(2-methyl-5-azapentalene)(2-n-butyl-4-(4'-tert-butyl-phenyl)-indenyl)- zirconiumdichloride,

A-(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tert-butyl-phenyl)-indenyl)- zirconiumdichloride,

A-(2-methyl-4-azapentalene)(2-methylindenyl) zirconiumdichloride,

A-(2-methyl-N-phenyl-4-azapentalene)(2-methylindenyl) zirconiumdichloride,

A-(2-methyl-4-thiapentalene)(2-methylindenyl)zirconiumdichloride,

A-(2-methyl-5-thiapentalene)(2-methylindenyl)zirconiumdichloride,

A-(2-methyl-6-thiapentalene)(2-methylindenyl)zirconiumdichloride,

A-(2-methyl-4-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-5-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-6-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-N-phenyl-4-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-N-phenyl-5-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-N-phenyl-6-azapentalene)(indenyl) zirconiumdichloride,

A-(2,5-dimethyl-N-phenyl-6-azapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-4-thiapentalene)(indenyl)zirconiumdichloride,

A-(2-methyl-5-thiapentalene)(indenyl)zirconiumdichloride,

A-(2-methyl-6-thiapentalene)(indenyl)zirconiumdichloride,

A-(2,5-dimethyl-4-thiapentalene)(indenyl) zirconiumdichloride,

A-(2-methyl-4-azapentalene)(2-methyl-4-phenyl-indenyl) zirconiumdichloride,

A-(2-methyl-5-azapentalene)(2-methyl-4-phenyl-indenyl) zirconiumdichloride,

A-(2-methyl-6-azapentalene)(2-methyl-4-phenyl-indenyl) zirconiumdichloride,

A-(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-phenyl-indenyl) zirconiumdichloride,
 A-(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-phenyl-indenyl) zirconiumdichloride,
 A-(2-methyl-4-thiapentalene)(2-methyl-4-phenyl-indenyl)zirconiumdichloride,
 A-(2-methyl-5-thiapentalene)(2-methyl-4-phenyl-indenyl)zirconiumdichloride,
 A-(2-methyl-6-thiapentalene)(2-methyl-4-phenyl-indenyl)zirconiumdichloride,
 A-(2-methyl-4-oxapentalene)(2-methyl-4-phenyl-indenyl)zirconiumdichloride,
 A-(2-methyl-4-azapentalene)(2-methyl-4,5-benzo-indenyl) zirconiumdichloride,
 A-(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4,5-benzo-indenyl) zirconiumdichloride,
 A-(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4,5-benzo-indenyl) zirconiumdichloride,
 A-(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4,5-benzo-indenyl) zirconiumdichloride,
 A-(2-methyl-4-thiapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-(2-methyl-5-thiapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-(2-methyl-6-thiapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-(2-methyl-4-oxapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-(2-methyl-5-oxapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-(2-methyl-6-oxapentalene)(2-methyl-4,5-benzo-indenyl)zirconiumdichloride,
 A-bis(2-methyl-4-azapentalene)zirconiumdichloride,
 A-bis(2-methyl-N-phenyl-4-azapentalene) zirconiumdichloride,
 A-bis(2-methyl-4-thiapentalene)zirconiumdichloride[[.]] ,

wherein

A is selected from the group consisting of structural isomers of Dipropylsilanediyl,
 Dibutylsilanediyl, Dipentylsilanediyl, Dihexylsilanediyl, Diheptylsilanediyl, Dioctylsilanediyl,
 Dinonylsilanediyl, Didecylsilanediyl, Diundecylsilanediyl, Didodecylsilanediyl,
 Di(cyclopentyl)silanediyl, Cyclohexyl(methyl)silanediyl, Dipropylgermanediyl,
 Dibutylgermanediyl, Dipentylgermanediyl, Dihexylgermanediyl, Diheptylgermanediyl,
 Dioctylgermanediyl, Dinonylgermanediyl, Didecylgermanediyl, Diundecylgermanediyl or
 Didodecylgermanediyl, Hexyl(methyl)germanediyl, Butyl(methyl)silanediyl,

Butyl(ethyl)silanediyl, Butyl(propyl)silanediyl, Pentyl(methyl)silanediyl, Pentyl(ethyl)silanediyl, Pentyl(propyl)silanediyl, Hexyl(methyl)silanediyl, Hexyl(ethyl)silanediyl and Hexyl(propyl)silanediyl.


28. (Original) The composition of Claim 27 where the units A are:

Di-n-propylsilanediyl, Di-n-butylsilanediyl, Di-n-pentylsilanediyl, Di(cyclopentyl)silanediyl, Di-n-hexylsilanediyl, Cyclohexyl(methyl)silanediyl, (n-butyl)(methyl)silanediyl or (n-hexyl)(methyl)silanediyl.

29. (Canceled)

30. (Previously presented) A process for the production of a mixture of racemic and meso isomers of metallocene compounds comprising the steps of:


a) providing a ligand system of the formula



(formula LS)

wherein

R⁹ is a bridge having one of the structures:




where R^{40} and R^{41} , are identical or different, with or without heteroatoms, when R^{40} and R^{41} are identical they are selected from the group consisting of an alkyl group having from 2 to about 30 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from about 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, when R^{40} and R^{41} are different one of either R^{40} and R^{41} is selected from the group consisting of an alkyl group having from 4 to about 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, and the other of R^{40} and R^{41} is selected from the group consisting of an alkyl group having from 1 to 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms an aryloxy group of

from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms,

M^{12} is silicon, germanium or tin, and

$R^3, R^4, R^5, R^6, R^7, R^8$ and also $R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'}$ and $R^{8'}$ are identical or different and are each a hydrogen atom, or a linear, cyclic or branched group, with or without heteroatoms, selected from the group consisting of an alkyl group of from 1 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or an arylalkenyl group of from 8 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group, with the proviso that R^3 and $R^{3'}$ are not hydrogen, or wherein two adjacent radicals R^5, R^6 or $R^{5'}, R^{6'}$, or R^6, R^7 or $R^{6'}, R^{7'}$, or R^7, R^8 or $R^{7'}, R^{8'}$ can form one or more hydrocarbon ring system(s),

wherein said ligand system is produced by deprotonation of a compound of the formula



(formula 2)

with a base in an inert solvent at temperatures of $-70\text{ }^{\circ}\text{C}$ to $80\text{ }^{\circ}\text{C}$; and,

b) combining said ligand system of formula LS with a compound having the formula M^1X_4 at a temperature of from about $-70\text{ }^{\circ}\text{C}$ to about $80\text{ }^{\circ}\text{C}$, wherein M^1 is zirconium, titanium or hafnium and X is a halogen, to provide a metallocene compound(s) having a weight ratio of racemic to meso isomers of greater than 5:1 as synthesized.

31. (Original) The process of Claim 30 wherein the weight ratio of racemic to meso


isomers is greater than 10:1 without any further separation of racemic from meso isomers.

32. (Original) The process of Claim 30 wherein the weight ratio of racemic to meso isomers is greater than 15:1 without any further separation of racemic from meso isomers.

33. (Original) The process of Claim 30 wherein the weight ratio of racemic to meso isomers is greater than 20:1 without any further separation of racemic isomers from meso isomers.

34. (Previously presented) A catalyst composition comprising:

a) mixed isomers of at least one metallocene compound having the formula 1a:




where L^1 and L^2 are identical or different ligands and are each a substituted mononuclear or polynuclear hydrocarbon radical selected from the group consisting of substituted cyclopentadienyl, indenyl, tetrahydroindenyl, azurenyl, fluorenyl, azapentalenyl, thiapentalenyl or oxapentalenyl, which form a sandwich structure with atom M^1 , therebetween,

R^1 and R^2 are identical or different and are each a hydrogen atom, an alkyl group of from 1 to about 10 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an aryloxy group of from about 6 to about 10 carbon atoms, an alkenyl group of from 2 to about 10 carbon atoms, an OH group, a halogen atom, or a NR_2^{32} group, where R^{32} is an alkyl group of from 1 to about 10 carbon atoms or an aryl group of from 6 to about 14 carbon atoms, or R^1 and R^2 form one or more ring system(s),

M^1 is a metal of group IVb of the Periodic Table of the Elements,

R^9 is a bridge between the ligands L^1 and L^2 having one of the structures:



where R^{40} and R^{41} , are identical or different, with or without heteroatoms, when R^{40} and R^{41} are identical they are selected from the group consisting of an alkyl group having from 2 to about 30 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from about 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, when R^{40} and R^{41} are different one of either R^{40} and R^{41} is selected from the group consisting of an alkyl group having from 4 to about 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms, an aryloxy group of from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms, and the other of R^{40} and R^{41} is selected from the group consisting of an alkyl group having from 1 to 40 carbon atoms, a fluoroalkyl group of from 2 to about 10 carbon atoms, an alkoxy group of from 2 to about 10 carbon atoms an aryloxy group of



from 6 to about 10 carbon atoms, an alkenyl group of from 3 to about 10 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms, a substituted or unsubstituted alkylsilyl or arylsilyl group and an arylalkenyl group of from 8 to about 40 carbon atoms,

M^{12} is silicon, germanium or tin, and


wherein the compound as synthesized has a ratio of racemic or pseudoracemic isomers to meso or pseudomeso isomers of greater than 5:1;

- b) at least one cocatalyst; and
- c) at least one porous support.

35. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is an aluminoxane having one of the following formulas




or,



wherein R is hydrogen, an alkyl group of from 1 to about 6 carbon atoms, an aryl group of from 6 to about 18 carbon atoms, or benzyl, and p is an integer from 2 to 50.

36. (Original) The catalyst composition system of Claim 35 wherein the atomic ratio of aluminum from the aluminoxane to the metal M¹ of the metallocene ranges from about 10:1 to about 1000:1.

37. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is a Lewis acid having the formula



wherein M^2 is selected from boron, aluminum or gallium, and

X¹, X² and X³ are the same or different and are each individually hydrogen, an alkyl group of from 1 to about 20 carbon atoms, an aryl group of from 6 to about 15 carbon atoms, or an alkaryl, aralkyl, halo-alkyl or haloaryl group having 1 to about 10 carbon atoms in the alkyl radical and from 6 to about 20 carbon atoms in the aryl radical, wherein the halogen component can be fluorine, chlorine, bromine or iodine.

38. (Currently amended) The catalyst composition of Claim 34 wherein the Lewis acid is selected from the group consisting of trimethylaluminum, triethylaluminum, triisobutylaluminum, tributylaluminum, trifluoroborane, triphenylborane, tris(4-fluorophenyl)borane, tris(3,5-difluorophenyl)borane, tris(4-fluoromethylphenyl)borane, tris(2,4,6-trifluorophenyl)borane, tris(~~penta-fluorophenyl~~ pentafluorophenyl)borane,

~~tris(tolyl)borane~~ tritolylborane, tris(3,5-dimethyl-phenyl)borane, tris(3,5-difluorophenyl)borane and tris (3,4,5-trifluorophenyl)borane.



39. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is an ionic compound containing a non-coordinating anion selected from the group consisting of tetrakis (pentafluorophenyl) borate, tetraphenylborate, SbF_6^- , CF_3SO_3^- and ClO_4^- .


40. (Original) The catalyst composition of Claim 34 wherein the porous support is selected from the group consisting of inorganic oxides, inorganic salts, and polymer powders.

41. (Currently amended) The catalyst composition of Claim 34 wherein the porous support is selected from the group consisting of silica, alumina, aluminosilicates, zeolites, MgO, ZrO_2 , TiO_2 , B_2O_3 , CaO, ZnO, ThO_2 , Na_2O , K_2O , Li_2O , Na_2CO_3 , K_2CO_3 , CaCO_3 , MgCl_2 , Na_2SO_4 , ~~$\text{Al}_2(\text{SO}_4)_3$~~ $\text{Al}_2(\text{SO}_4)_3$, BaSO_4 , KNO_3 , $\text{Mg}(\text{NO}_3)_2$; ~~$\text{Al}(\text{NO}_3)_3$~~ $\text{Al}(\text{NO}_3)_3$ and combinations thereof.


42. (Currently amended) The catalyst system of Claim 34 wherein the porous support is selected from the group consisting of polyethylene, polypropylene, polybutene, polystyrene, divinylbenzene crosslinked polystyrene, polyvinyl chloride, acrylonitrile-butadiene-styrene copolymer, polyamide, polymethacrylate, polycarbonate, polyester, polyacetal ~~or~~ and polyvinyl alcohol.

43. (Currently amended) The catalyst composition of Claim 34 wherein the cocatalyst is a reaction product of at least one compound of formulas (C) and/or (D) and/or (E) with at least one compound of formula (F),





(E)



(F)

where



R^{27} is a hydrogen atom or a boron-free C_1 - C_{40} carbon-containing group, selected from an alkyl group of from 1 to about 20 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms or an alkylaryl group of from 7 to about 40 carbon atoms,

R^{17} and R^{18} are the same or different and are a hydrogen atom, a halogen atom, or a C_1 - C_{40} carbon-containing group, selected from an alkyl group of from 1 to about 20 carbon atoms, a haloalkyl group of from 1 to about 20 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, a haloaryl group of from 6 to about 20 carbon atoms, an aryloxy group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, a haloarylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or a haloalkylaryl group of from 7 to about 40 carbon atoms or R^{17} may also be an $-\text{OSiR}^{51}_3$ group, in which the R^{51} groups are the same or different and ~~have the same meaning as R^{17}~~ ; are each a hydrogen atom, a halogen atom, or a C_1 - C_{40} carbon-containing group, selected from an alkyl group of from 1 to about 20 carbon

atoms, a haloalkyl group of from 1 to about 20 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, a haloaryl group of from 6 to about 20 carbon atoms, an aryloxy group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, a haloarylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or a haloalkylaryl group of from 7 to about 40 carbon atoms,

- D is an element of main Group VI of the periodic table of elements or an NR^{61} group, where R^{61} is a hydrogen atom or a $\text{C}_1\text{-C}_{20}$ hydrocarbon group, selected from an alkyl group of from 1 to about 20 carbon atoms or an aryl group of from 6 to about 20 carbon atoms,
- f is a whole number from 0 to 3,
- g is a whole number from 0 to 3 with $z+y$ $f+g$ not equal to 0, and
- h is a whole number from 1 to 10.


44. (Currently amended) The catalyst composition of Claim 34 wherein the cocatalyst is a compound or a mixture of compounds of formulas (A) and/or (B)








where R^{17} and R^{18} are the same or different and are a hydrogen atom, a halogen atom, a $\text{C}_1\text{-C}_{40}$

carbon-containing group, selected from an alkyl group of from 1 to about 20 carbon atoms, a haloalkyl group of from 1 to about 20 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, a haloaryl group of from 6 to about 20 carbon atoms, an aryloxy group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, a haloarylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or a haloalkylaryl group of from 7 to about 40 carbon atoms or R^{17} may also be an $-\text{OSiR}^{51}_3$ group, where the R^{51} groups are the same or different and ~~have the same meaning as R^{17}~~ are each a hydrogen atom, a halogen atom, a C_1 - C_{40} carbon-containing group, selected from an alkyl group of from 1 to about 20 carbon atoms, a haloalkyl group of from 1 to about 20 carbon atoms, an alkoxy group of from 1 to about 10 carbon atoms, an aryl group of from 6 to about 20 carbon atoms, a haloaryl group of from 6 to about 20 carbon atoms, an aryloxy group of from 6 to about 20 carbon atoms, an arylalkyl group of from 7 to about 40 carbon atoms, a haloarylalkyl group of from 7 to about 40 carbon atoms, an alkylaryl group of from 7 to about 40 carbon atoms or a haloalkylaryl group of from 7 to about 40 carbon atoms .


45. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is a compound or a mixture of compounds of the following formulas








46. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is



47. (Original) The catalyst composition of Claim 34 wherein the cocatalyst is



48. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 43.

49. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 44.

50. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 45.

51. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 46.

52. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 47.

53. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from about 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 34.

54. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 35.

55. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 36.

56. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 37.

57. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 38.

58. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 39.


59. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 40.

60. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 41.

61. (Original) A process for the polymerization of olefins comprising contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with the catalyst composition of Claim 42.

62. (Original) The process of Claim 53 wherein at least one olefin is a 1-olefin.

63. (Original) The process of Claim 53 wherein at least one olefin has the formula



wherein R^m and R^n can be identical or different and are each individually a hydrogen atom or a radical having from 1 to about 20 carbon atoms or R^m and R^n together can form one or more rings.

64. (Original) The process of Claim 53 wherein the olefins include ethylene and one or more 1-olefins having from 4 to about 20 carbon atoms.

65. (Original) The process of Claim 53 wherein the olefins include propylene.

66. (Original) The process of Claim 53 wherein the olefins include propylene and ethylene.

67. (Original) The process of Claim 53 wherein the olefins include propylene and one or more 1-olefins having from 4 to about 20 carbon atoms.

68. (Original) The process of Claim 53 wherein the olefins include propylene, ethylene and one or more 1-olefins having from 4 to about 20 carbon atoms.

69. (Original) A process for the polymerization of olefins comprising:
contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with a catalyst composition including at least one compound having the formula 1a as set forth in claim 1.

70. (Original) A process for the polymerization of olefins comprising:
contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with a catalyst composition including at least one compound having the formula 1b as set forth in claim 9.

71. (Original) A process for the polymerization of olefins comprising:
contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with a catalyst composition including at least one compound having the formula 1c as set forth in claim 15.

72. (Original) A process for the polymerization of olefins comprising:
contacting one or more olefins each having from 2 to about 20 carbon atoms under polymerization reaction conditions with a catalyst composition including at least one compound having the formula 1d as set forth in claim 22.